

Structural Studies of the Fe/ La₂O₃ nanocomposite obtained by mechanochemical milling.

S. Lalaoua, B. Bouzabata

Laboratoire Magnétisme et Spectroscopie des Solides (LM2S), Université Badji-Mokhtar de Annaba, B.P.12, Annaba, Algérie.

samira.lalaoua@univ.annaba.org

Abstract

Rare-earth oxides as Y₂O₃ and La₂O₃ evenly dispersed in Fe matrix constitute ODS alloys with potential applications in nuclear power plants. Dispersion of the above oxides can be obtained from various synthetic routes. However, kinetics, particle size and morphology are difficult to control. Mechanochemical activation of rare earth oxide precursors with either Fe₂O₃ (hematite) or Fe₃O₄ (magnetite) was also used since diffusive processes are accelerated under ambient conditions. In the induced chemical reaction, AFeO₃ oxides (A is a rare earth element) can also be produced. This last orthoferrite phase is also interesting for its wide magnetic applications.

In this work, Fe/ La₂O₃ composite powder has been fabricated by high energy ball milling. Powder mixtures were milled during different times 0, 5, 10h in a planetary ball mill where hardened steel vials were rotated at about 400 rpm under argon atmosphere and a ball to powder weight ratio of 16:1. And phase evolution of the milled powder mixtures were analyzed during the mechanical treatment by X-ray diffraction, differential thermal analysis and scanning microscopy.

Results showed that for the Fe/10%wt. La₂O₃ composite, starting powders are Fe, La₂O₃ and La(OH)₃. The last one is due to the highly hygroscopic of La₂O₃, that convert to La(OH)₃ when exposed to air. Also, the best refinement of X-ray diffraction pattern shows that La₂O₃ is composed of two structures cubic and hexagonal. After 5h of milling, the formation of the perovskite LaFeO₃ is observed with the presence of nanocrystalline Fe and La₂O₃ phases. Increasing the milling time transforms the oxide phase into an amorphous structure and the iron phase into a disordered phase with a grain size less than 20 nm. Above 10 h of milling, the orthoferrite LaFeO₃ disappears. Thermal analysis showed the presence of two endothermic peaks of La(OH)₃ at 350 and 500°C. Increasing the milling time to 10h

, the formation of a wide exothermic peak is observed due mainly to LaFeO₃.